

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of Claims:

1. (Canceled)

2. (Currently Amended) A pressure-sensitive adhesive sheet for removal of a solvent-containing substance by sticking to and peeling off from an article to be cleaned, the sheet comprising a substrate and a pressure-sensitive adhesive layer, ~~excluding a foaming pressure sensitive adhesive layer,~~ formed at least on one side of the substrate, wherein the pressure-sensitive adhesive layer is solid and comprises an adhesive of either (A) or (B):

(A) an acrylic pressure-sensitive adhesive comprising a base polymer formed by a base monomer of 40% to 98% by weight, a comonomer of 0% to 50% by weight, and a functional-group-containing monomer of 0.5% to 15% by weight of the total monomer components or

(B) a rubber pressure-sensitive adhesive selected from natural rubber pressure-sensitive adhesives, styrene-butadiene copolymers, polyisobutylene, and styrene-isoprene-styrene copolymers;

wherein said pressure-sensitive adhesive layer absorbs 5 g/m² or more of a solvent contained in the substance to be removed when the

pressure-sensitive adhesive sheet is immersed in the solvent for 1 second, and wherein the pressure-sensitive adhesive sheet after absorbing 5g/m^2 of the solvent has a tackiness of 3 cN/25-mm or more as determined by a method in conformity with Japanese Industrial Standards (JIS) Z 0237.

3. **(Previously Presented)** A pressure-sensitive adhesive sheet for removal of a solvent-containing substance by sticking to and peeling off from an article to be cleaned, the sheet comprising a substrate and a pressure sensitive adhesive layer formed at least on one side of the substrate,

wherein the pressure-sensitive adhesive layer comprises an adhesive of either (A) or (B):

(A) an acrylic pressure-sensitive adhesive comprising a base polymer formed by a base monomer of 40% to 98% by weight, a comonomer of 0% to 50% by weight, and a functional-group-containing monomer of 0.5% to 15% by weight of the total monomer components or

(B) a rubber pressure-sensitive adhesive selected from natural rubber pressure-sensitive adhesive, styrene-butadiene copolymers, polyisobutylene, and styrene-isoprene-styrene copolymers;

wherein said pressure-sensitive adhesive layer absorbs 5 g/m^2 or more of a solvent contained in the substance to be removed when the pressure-sensitive adhesive sheet is immersed in the solvent for 1

second, and wherein no stain is observed in a stainless steel plate (a SUS 430BA plate) by visual inspection when the pressure-sensitive adhesive sheet after absorbing 5 g/m² of the solvent is stuck to the stainless steel plate by a reciprocating motion of a 2-kg rubber roller and is peeled off from the stainless steel plate.

4-7. (Canceled)

8. (Currently Amended) The pressure-sensitive adhesive sheet for removal of a solvent-containing substance according to claim 2, ~~or 3,~~ wherein the pressure-sensitive adhesive layer before use has a tackiness of from 1 to 400 cN/25-mm as determined by a method in conformity with JIS Z 0237.

9-21. (Canceled)

22. (Currently Amended) The pressure-sensitive adhesive sheet for removal of a solvent-containing substance according to claim 2, ~~or 3,~~ wherein said acrylic pressure-sensitive adhesive comprises the polymer in adhesive (A) obtained by polymerizing the monomer mixture, and

wherein the base monomer is at least one selected from the group consisting of acrylic C₂-C₁₀ alkyl esters,

the comonomer is at least one selected from the group consisting of methyl acrylate, alkyl methacrylates, vinyl esters, styrenic monomers, and acrylonitrile, and

the functional-group-containing monomer is at least one selected from the group consisting of carboxyl group containing monomers, acid anhydride group containing monomers, hydroxyl group containing monomers, epoxy group containing monomers, amido group containing monomers, and amino group containing monomers.

23. **(Currently Amended)** The pressure-sensitive adhesive sheet for removal of a solvent-containing substance according to claim 2, ~~or 3,~~ wherein said pressure-sensitive adhesive layer comprises a pressure-sensitive adhesive polymer and a crosslinking agent in the amount of from 1 to 30 parts by weight relative to 100 parts by weight of the pressure-sensitive adhesive polymer.

24. **(New)** The pressure-sensitive adhesive sheet for removal of a solvent-containing substance according to claim 2 or 3, wherein said pressure-sensitive adhesive layer consists essentially of

the adhesive (A) or adhesive (B), and

at least one additive selected from the group consisting of a crosslinking agent, tackifier, surfactant, plasticizer, antioxidant, coloring agent, antistatic agent and filler.

25. **(New)** The pressure-sensitive adhesive sheet for removal of a solvent-containing substance according to claim 2 or 3, wherein said pressure-sensitive adhesive sheet further comprises at least one additive selected from the group consisting of a crosslinking agent, tackifier, surfactant, plasticizer, antioxidant, coloring agent, antistatic agent and filler.

26. **(New)** The pressure-sensitive adhesive sheet for removal of a solvent-containing substance according to claim 3, wherein the pressure-sensitive adhesive layer before use has a tackiness of from 1 to 400 cN/25-mm as determined by a method in conformity with JIS Z 0237.

27. **(New)** The pressure-sensitive adhesive sheet for removal of a solvent-containing substance according to claim 3, wherein said acrylic pressure-sensitive adhesive comprises the polymer in adhesive (A) obtained by polymerizing the monomer mixture, and

wherein the base monomer is at least one selected from the group consisting of acrylic C₂-C₁₀ alkyl esters,

the comonomer is at least one selected from the group consisting of methyl acrylate, alkyl methacrylates, vinyl esters, styrenic monomers, and acrylonitrile, and

the functional-group-containing monomer is at least one selected from the group consisting of carboxyl group containing monomers, acid

Appl. No. 09/936,930

Art Unit 1771

Reply to Office Action of July 28, 2004

anhydride group containing monomers, hydroxyl group containing monomers, epoxy group containing monomers, amido group containing monomers, and amino group containing monomers.

28. **(New)** The pressure-sensitive adhesive sheet for removal of a solvent-containing substance according to claim 3, wherein said pressure-sensitive adhesive layer comprises a pressure-sensitive adhesive polymer and a crosslinking agent in the amount of from 1 to 30 parts by weight relative to 100 parts by weight of the pressure-sensitive adhesive polymer.